

Ver 03 - PALSFL 07.07.21

SUPER-FLEX

UNIQUE RUBBER REINFORCED & POLYMER MODIFIED ADHESIVE

- HIGHLY POLYMER MODIFIED TO TOLERATE SLIGHT MOVEMENT & DEFORMATION
- FIXES ALL TYPES OF TILE TO SUBSTRATES WHICH MAY BE PRONE TO VIBRATION
- MIXES TO GIVE A LIGHTWEIGHT HIGH YIELD EASY TO APPLY PASTE
- DUST-REDUCED FORMULA MINIMISES AIRBORNE POWDER CONTAMINATION
- FIXES TILES WHERE ALL TYPES OF SUB-FLOOR HEATING ARE INSTALLED

TECHNICAL SUMMARY

UNIT SIZES	15kg
COLOURS	Grey
MEAN BED DEPTH	Up to 6mm
TIME UNTIL READY TO GROUT	4 hours*
WORKING POT LIFE	1 hour*
INITIAL SET TIME	3 hours*
APPLICATION TEMPERATURES	5°C - 25°C

* More information can be found within data sheet



PALACE SUPER FLEX LIGHTWEIGHT

Is a unique rubber reinforced & polymer modified adhesive, with excellent application mix yield when mixed with water for fixing ceramic floor and wall tiles, including mosaics, porcelain and vitrified tiles onto challenging surfaces in interior & exterior locations.

REDUCED
DUST

FIXES TILE TO SUBSTRATE
PRONE TO VIBRATION

SUPER-FLEX

Unique Rubber Reinforced & Polymer Modified Adhesive

DESCRIPTION

PALACE SUPER-FLEX S2 LIGHTWEIGHT is a highly polymer reinforced cement-based, fast setting, thin-bed wall & floor tile adhesive, which conforms to BS EN 12004 Type C, Class 2FTE-S2. It is recommended when fixing ceramic and stone FLOOR and WALL tiles, in some of the most heavily trafficked interior & exterior locations where movement & vibration can be expected. **PALACE SUPER-FLEX S2 LIGHTWEIGHT** has a 1-hour working pot-life with an extended "wet-tack" open time and rapidly cures to an initial set at 2 hours which allows foot traffic after three hours. **PALACE SUPER-FLEX S2 LIGHTWEIGHT** cures to a high bond strength, with excellent water-resistance and is also recommended in frequently wet & immersed area.

SURFACE PREPARATION

The substrate must be clean, dry, firm and free of dust, dirt, oil, grease and loose flaking coatings. It must also be structurally sound and strong enough to support the expected traffic loading. Wood based surfaces, plywood, panel-boards and tongue & groove floorboards should be dry, sealed on all exposed faces and edges and then primed using **TILERS PRIMER SBR** diluted 1 to 1 with water. Timber boarding should then be over-laid with Tile Backer boards, screw fixed to support battens at 300mm centres to provide a dimensionally stable background as described in BS 5385 Part 1. All boards must be level, showing no edge protrusions and be fixed in place with a 0.5 to 1mm gap to avoid expansion stresses between the boards and around the wall perimeters. Do not apply onto bare, un-sealed gypsum plaster or anhydrite floor screed before first priming this type surface with two coats of neat **PALACE TILERS PRIMER** the first diluted 1 to 1 and the second neat.

MIX PREPARATION

PALACE SUPER-FLEX S2 LIGHTWEIGHT should be added to water in a clean container whilst mechanically stirring and mixed thoroughly to give a soft, slump-free, easily worked mortar. The recommended mixing proportions by volume are approximately 5.5 litres of water per 15kg. The consistency of the paste can be adjusted with slight additions of water or powder at the initial mixing stage, however part-used adhesive should never be "freshened up" with later water additions but should always be discarded when it loses its workability. In ideal conditions (20°C room temperature), **PALACE SUPER-FLEX S2 LIGHTWEIGHT** will remain workable for up to 1 hour at 20°C and then reach final set after 3 - 4 hours, after which time it is sufficiently well cured to permit grout application on both walls & floors.

APPLICATION METHOD

For fixing ceramic tiles or mosaics, use a notched trowel to give a ribbed mortar bed on the substrate, into which the tiles are firmly bedded with a twist and slide action to ensure full contact. Use a 3mm x 3mm notch at 6mm centres for mosaics and thin flat backed wall tiling, a 5mm x 5mm notch at 10mm centres for general wall tiling and 10mm x 10mm notch at 16mm centres for floor tiling. The position of the tiles can be adjusted up to 10 minutes after initial fixing. Open time of the exposed mortar bed is approximately 30 minutes and it is recommended that tiles with raised or studded back profiles, should be back-buttered to ensure solid bed fixing. Do not trowel out an area of adhesive greater than can be tiled over within a 30-minute period. Surfaces, such as tamped concrete and masonry block-work, that are uneven should be prepared with **PALACE SELF-LEVEL** floor smoothing & levelling compound and when sufficiently firm (24 - 48 hours later), followed by an application of **PALACE SUPER-FLEX S2 LIGHTWEIGHT** adhesive. Do not apply any cement-based adhesive onto bare, unsealed gypsum plaster or anhydrite screeds and do not allow adhesive residues to set & harden on the tile face. Do not mix or apply this adhesive when air or ground temperatures are forecast to be below 5°C or greater than 35°C at any time during the first 24 hours after application.

COVERAGE

When fixing on a level, even surface using a 10mm notched trowel, **PALACE SUPER-FLEX S2 LIGHTWEIGHT** will cover at a rate of about 3.0 - 4.0kg per sq. mtr for heavy-duty, studded tiles. When applying wall tiles, the product will cover at about 1.8 - 2.2 kg per sq. mtr.

GROUTING

Grouting may proceed as soon as the tile bed is sufficiently firm, which for **PALACE SUPER-FLEX S2 LIGHTWEIGHT** will be after 3 hours at room temperature. This period however will be extended in cold conditions. When the adhesive is fully set, wall & floor joints can be grouted using **PALACE COLOUR-LOCK GROUT** or **PALACE ANTI-MOULD GROUT**, however on wider flooring applications, joints of up to 20mm wide can be grouted using **PALACE WIDE JOINT FLEXI FLOOR TILE GROUT**.



EN ISO 14001



EMS 85788

EN ISO 9001



FM 01010

EN ISO 18001



OHS 596309

PALACE CHEMICALS LTD

SPEKE HALL INDUSTRIAL ESTATE

SPEKE LIVERPOOL L24 1YA

TEL: 0151 486 6101 - FAX: 0151 448 1982

E-MAIL: SALES@PALACECHEMICALS.CO.UK

SUPER-FLEX

Unique Rubber Reinforced & Poylmer Modified Adhesive

STORAGE AND PACKAGING

PALACE SUPER-FLEX S2 LIGHTWEIGHT is supplied in 15kg multi-ply, moisture resistant paper sacks and has a storage life of not less than 12 months if stored in dry, un-opened conditions.

HEALTH AND SAFETY

Always ensure that appropriate PPE is worn when mixing & applying this product to ensure protection from airborne dust and skin contact with the mixed liquid product. Wash hands after use and launder stained clothing. Do not consume food when working with this material and keep children & animals away from any possible risk of contact. A complete PALACE material safety data sheet is available on request or online at www.palacechemicals.co.uk

QUALITY AND ENVIRONMENT

All Palace Chemicals products are manufactured under a BSI accredited ISO 9001:2015 Quality Management System, along with an ISO 14001 Environmental Management system continually working to reduce our carbon footprint.

TECHNICAL ADVISORY SERVICE

Should more specific technical information be required, contact the Palace Technical helpline on: **0151 486 6101**.

For a Technical Specification and quantity requirements, visit our 'TilingSpecifier' on the Palace website at: <http://www.palacechemicals.co.uk>

TECHNICAL SUMMARY	
UNIT SIZE	15kg
COLOURS	Grey
MEAN BED DEPTH	Up to 6mm
TIME UNTIL READY TO GROUT	4 hours*
WORKING POT LIFE	1 hour*
INITIAL SET TIME	3 hours*
APPLICATION TEMPERATURES	5 – 25°C

* Dependent on temperature of substrate and site conditions

WALL TILES SUBSTRATE LOAD LIMITS

Wall substrates should be strong enough to support the weight of the ceramic tile or natural stone to be installed and the weight of the associated adhesive bed. The maximum weight restrictions for wall substrates are given below...

DESCRIPTION	KG/M ²
GYPSUM PLASTER (sealed with Tilers Primer)	20.0
GYPSUM PLASTERBOARD (12.5 mm)	32.0
CEMENT / SAND RENDERING & CONCRETE	No Limit
LIGHTWEIGHT FOAM-CORED TILE BACKER BOARDS	60.0
GLASS REINFORCED CEMENT-BASED BOARDS	50.0
GYPSUM FIBREBOARDS	40.0
OTHER RIGID TILE BACKER BOARDS	#

Consult the manufacturer

APPROVED RECEIVING SURFACES
✓ Concrete
✓ Sand/cement screed
✓ Tile backer boards
✓ Anhydrite / gypsum-based screeds
✓ Firm and stable plaster (sealed)**
✓ Plasterboard
✓ Sand/cement render
✓ Green screeds
✓ Existing tiles
✓ Vinyl tiled surfaces
✓ Concrete brick/block

* Must be securely fixed

** Sealed with TILERS PRIMER



EN ISO 14001



EMS 85788

EN ISO 9001



FM 01010

EN ISO 18001



OHS 596309

PALACE CHEMICALS LTD

SPEKE HALL INDUSTRIAL ESTATE


SPEKE LIVERPOOL L24 1YA

TEL: 0151 486 6101 – FAX: 0151 448 1982

E-MAIL: SALES@PALACECHEMICALS.CO.UK

SUPER-FLEX

Unique Rubber Reinforced & Poylmer Modified Adhesive

	
PALACE CHEMICALS LTD SPEKE HALL INDUSTRIAL ESTATE SPEKE LIVERPOOL L24 1YA	
EN 12004 - C2FTE-S2 Improved fast setting deformable cementitious adhesive with extended open time & reduced slip	
EARLY TENSILE ADHESION STRENGTH	> 0.5 N/mm ²
INITIAL TENSILE ADHESION STRENGTH AT 30 MINS OPEN TIME	> 0.5 N/mm ²
INITIAL TENSILE ADHESION STRENGTH	> 1.0 N/mm ²
TENSILE ADHESION STRENGTH AFTER HEAT AGEING	> 1.0 N/mm ²
TENSILE ADHESION STRENGTH AFTER FREEZE THAW CYCLES	> 1.0 N/mm ²
TENSILE ADHESION STRENGTH AFTER WATER IMMERSION	> 1.0 N/mm ²
DEFORMATION	> 5.0mm
REDUCED SLIP	< 0.5mm
REACTION TO FIRE	NPD

DISCLAIMER

The information provided by this Technical data sheet is given in good faith and is to the best of our current knowledge true and accurate, however it is given without guarantee, as conditions of use and workmanship involved are both beyond our control. All information supplied is subject to the company's terms and conditions of sale, copies of which are available on request.



EN ISO 14001



EMS 85788

EN ISO 9001



FM 01010

EN ISO 18001



OHS 596309

PALACE CHEMICALS LTD

SPEKE HALL INDUSTRIAL ESTATE

SPEKE LIVERPOOL L24 1YA

TEL: 0151 486 6101 - FAX: 0151 448 1982

E-MAIL: SALES@PALACECHEMICALS.CO.UK