

Ver 03 - PALGF 30.06.21

GOLD-FIX

READY MIXED NON-SLIP WALL TILE ADHESIVE

- FOR INTERIOR USE
- FOR WALL TILE FIXING
- FOR VITRIFIED AND PORCELAIN TILES
- SUITABLE FOR ALL SUBSTRATES
- EXCELLENT INITIAL GRAB
- NON-SLIP



TECHNICAL SUMMARY

APPEARANCE	Smooth off-white paste
NON-SLIP	For most tile sizes
OPEN TIME	20 minutes
INITIAL DRYING TIME	24 hours (porous walls)*
COVERAGE	1.6kg per m ² *

* Dependent on temperature of substrate and site conditions

PALACE GOLD-FIX

Is an off-white ready mixed adhesive for wall tile fixing of mosaics and tiles in bathrooms, kitchens and domestic shower areas. GOLDFIX adheres to most wall surfaces, is easy to apply and has excellent spreading & non-slip characteristics to suit both the DIY and professional use.

EASY TO APPLY

SUITABLE FOR ALMOST ALL SURFACES

GOLD-FIX

Ready Mixed Non-Slip Wall Tile Adhesive



DESCRIPTION

PALACE GOLD-FIX is an off-white ready mixed adhesive paste, for use as a thin-bed ceramic tile adhesive and conforms to BS 5980 Type 2 Class B (BS EN 12004 Type D, Class 1T). Suitable for fixing all types of ceramic wall tiles, including mosaics, porcelain and vitrified tiles in internal locations such as bathrooms, kitchens and domestic shower areas. **PALACE GOLD-FIX** can be applied to gypsum plaster, plasterboards, cement fibreboard, existing tiles, cement render, concrete blockwork, timber panels and plywood composite boards. **PALACE GOLD-FIX** provides the tiler with an easy to apply, general purpose adhesive with spreading characteristics, which suit both the DIY and professional user.

SURFACE PREPARATION

All surfaces must be clean, firm and free of dust, dirt, oil, grease and loose flaking coatings. Gypsum finishing plaster should be at least 4 to 6 weeks old, thoroughly dry and wiped clean of dust, efflorescence and loose flaking material. Highly polished (shiny) plaster surfaces should be roughened with a stiff brush, removing all loose fines. All plaster and porous masonry surfaces should be primed with **TILERS PRIMER SBR** diluted as 1 part to 3 parts with water and allowed to dry. All wood based surfaces, (plywood and composite panel-boards) should be dry, sealed on all exposed faces and edges and then primed using **TILERS PRIMER SBR** diluted as 1 to 3 parts water. Timber boarding should be waterproof rated, 15mm thick and be screw fixed at 300mm centres to provide a dimensionally stable background as described in BS 5385. All boards must be level, showing no edge protrusions and be fixed in place with a 0.5 to 1mm gap to avoid expansion stresses between the boards and around the wall corners. Expansion joints should be installed in accordance with the recommendations of BS 5385. Remove areas of unsound (emulsion based) paint from walls and when tiling over existing tiles ensure they are securely fixed in all areas. Thoroughly clean and dry tiled, or non-porous surfaces and slightly score out joints to provide a key.

APPLICATION METHOD

PALACE GOLD-FIX is intended for application by a notched trowel (5mm x 5mm notch at 10 - 25mm centres) to give a ribbed bed on the wall surface, into which the tiles are firmly bedded with a twist and slide action to ensure complete contact. The position of the tiles can be adjusted up to 10 minutes after initial fixing. Open time of the exposed adhesive bed is approximately 20 minutes, depending on surface porosity and site conditions, however in warm

rooms this period may be reduced – check the adhesive remains “tacky to touch” as fixing proceeds. Do not trowel out an area of adhesive greater than can be tiled over within a 10 minute period (about 1 square metre). The final adhesive bed depth should be in the range of 2 to 3mm and grout joints should be at least 2mm, unless self-spacing tiles are used. Ensure all adhesive residues remaining on the tile face are wiped clean with a moist cloth as fixing proceeds, and rake out any excess adhesive from within the grout joints. **PALACE GOLD-FIX** should not be applied onto walls affected by penetrating damp, in areas of persistently high humidity or when the room temperature is below 5°C. When fixing porcelain tiles the drying time of the adhesive will be significantly extended therefore grouting should be delayed until the adhesive is fully dry, additionally any porcelain tiles of size 300mm x 300mm or greater should ideally be fixed using a cement based adhesive. Additionally, all types of large format ceramic tile, i.e. those with dimensions of 300mm x 400mm or more, will also significantly prolong the drying time of this adhesive and a cement based alternative is strongly recommended in such circumstances.

COVERAGE

Depends on surface texture and porosity, however on a typical smooth plastered wall **PALACE GOLD-FIX** will cover at a rate of 1.6kg per square metre.

GROUTING

Grouting may proceed as soon as the tile bed is sufficiently firm, which depending upon site conditions can be from 24 hours after fixing on porous surfaces such as plaster or up to 7 days where tiles have been fixed to an impermeable surface such as existing tiles or waterproof boards. These periods however may be prolonged in cold conditions. In areas subject to intermittent wetting, such as domestic showers, always use a waterproof grout such as **WHITE WALL TILE GROUT** or ready mixed **ACRYLIC GROUT**. Allow up to 14 days for both to fully dry out before subjecting the tiled area to contact with water.

STORAGE AND PACKAGING

PALACE GOLD-FIX is supplied in a 15 kg & 7.5 kg & (3.75 kg x 4); buckets and has a storage life of not less than 12 months if kept in dry, un-opened conditions.

HEALTH AND SAFETY

A complete PALACE material safety data sheet is available on request or online at www.palacechemicals.co.uk



EN ISO 14001



EMS 85788

EN ISO 9001



FM 01010

EN ISO 18001



OHS 596309

PALACE CHEMICALS LTD

SPEKE HALL INDUSTRIAL ESTATE

SPEKE LIVERPOOL L24 1YA

TEL: 0151 486 6101 – FAX: 0151 448 1982

E-MAIL: SALES@PALACECHEMICALS.CO.UK

GOLD-FIX

Ready Mixed Non-Slip Wall Tile Adhesive



QUALITY AND ENVIRONMENT


All Palace Chemicals products are manufactured under a BSI accredited ISO 9001:2015 Quality Management System, along with an ISO 14001 Environmental Management system continually working to reduce our carbon footprint.

TECHNICAL ADVISORY SERVICE

Should more specific technical information be required, contact the Palace Technical helpline on: **0151 486 6101**.

For a Technical Specification and quantity requirements, visit our 'TilingSpecifier' on the Palace website at: <http://www.palacechemicals.co.uk>

TECHNICAL SUMMARY	
APPEARANCE	Smooth off-white paste
NON-SLIP	For most tile sizes
OPEN TIME	20 minutes
INITIAL DRYING TIME	24 hours (porous walls)
COVERAGE	1.6kg per m ²

	
PALACE CHEMICALS LTD SPEKE HALL INDUSTRIAL ESTATE SPEKE LIVERPOOL L24 1YA	
EN 12004 – D1T Normal dispersion adhesive with reduced slip for tiling	
INITIAL SHEAR ADHESION STRENGTH	> 1.0 N/mm ²
SHEAR ADHESION STRENGTH AFTER HEAT AGEING	> 1.0 N/mm ²
OPEN TIME: TENSILE ADHESION STRENGTH (20 MINUTES)	> 0.5 N/mm ²
REDUCED SLIP	<0.5mm
REACTION TO FIRE	NPD

DISCLAIMER

The information provided by this Technical data sheet is given in good faith and is to the best of our current knowledge true and accurate, however it is given without guarantee, as conditions of use and workmanship involved are both beyond our control. All information supplied is subject to the company's terms and conditions of sale, copies of which are available on request.



EN ISO 14001



EMS 85788

EN ISO 9001



FM 01010

EN ISO 18001



OHS 596309

PALACE CHEMICALS LTD

SPEKE HALL INDUSTRIAL ESTATE

SPEKE LIVERPOOL L24 1YA

TEL: 0151 486 6101 – FAX: 0151 448 1982

E-MAIL: SALES@PALACECHEMICALS.CO.UK