


ISSUE: 11021 / 0317

BPD APPROVAL
No. UK-2016-1015**EFFECTIVE AGAINST**
DRY ROT & WOOD STAINING FUNGI**INTERIOR / EXTERIOR**
WOOD PRESERVATIVE

Description:

LANGLOW WOOD PRESERVATIVES are BPD approved, solvent based solutions of the anti-fungal active ingredients Propiconazole and IPBC Polyphase, available in CLEAR or colours such as RED CEDAR; DARK BROWN; GOLDEN BROWN; PALE GREEN & DARK GREEN. The low odour non-flammable carrier solvent enables this active to achieve deep penetration into most common sizes of structural timber, allowing the active ingredient to remain stable, effective and give long-term anti-fungal protection. LANGLOW WOOD PRESERVATIVES prevent the damage caused to timbers by "Serpula Lacrymans", the dry rot fungus or "Coniophora Puteana", the wet rot version, both of which can be found in any timbers (interior / exterior) where there has been prolonged exposure to excessive moisture levels in a poorly ventilated environment. They also protect against damage from water ingress due to the presence of water-repellent resins, which ensure greater durability for the active held within the timber, whilst still allowing the treated surface to be primed & over-painted with a protective weather-proof finish.

Colour Range:

DARK BROWN	GOLDEN BROWN	RED CEDAR	DARK GREEN	PALE GREEN	CLEAR
					

Preparation:

Ensure all timbers are structurally sound, dry and free from surface coatings (internal) or growths of moss, lichen and algae (external). Care should be taken within the property to remove or isolate all potential sources of ignition and to protect all surrounding fabrics and materials, cables etc, which may be susceptible to damage by the solvent, including any plants and foliage from contact with the product during external application. To ensure adequate penetration, all timbers to be treated must have a moisture content (when tested by conductivity meter) to be no more than 22%. All fabrication work, i.e. planing, sawing & boring should be completed prior to treatment and any post treatment cutting should be followed by an additional preserver application. Children and pets should also be kept away from treated timbers until they are completely dry and free of any traces of product.

Application:

LANGLOW WOOD PRESERVATIVES can be applied by brush, spray or dip methods using up to 3 consecutive coats to achieve deeper penetration and a darker colour shade where necessary. Use a broad-bristled brush and apply evenly, soaking the timbers to refusal to achieve best results. Spray applications should be made with a coarse droplet spray nozzle held within 300mm of the treated timber at all times to limit wastage and reduce the risk of contaminating surrounding plants and structures. Full immersion application requires joinery to be submerged completely in the product for a minimum of 10 minutes to give sufficient protection for timber to claim "long-term protection", providing it is to be installed above DPC level and receives a weatherproof protective top-coating. Always pay extra attention to ensuring exposed end-grain timbers are fully saturated. For timbers being set in the ground it is recommended to over-coat the submerged section with Bitumen Paint to protect against groundwater saturation. Do not apply to timber with a moisture content greater than 18% w/w and ensure the wood surface is dry, clean & free from loose coatings & decay. When treatment is complete the use of a protective finish top-coat is advised.

Coverage:

Depending upon the texture and porosity of the timber to be treated, LANGLOW WOOD PRESERVATIVE when applied as a single coat will cover at the rate of approximately 180 – 200ml per square metre [146 – 178 g/m²], either by brush or spray application method. Dipping, deluge or double vacuum impregnation should achieve consumption of treatment at 38 – 45 kg/M³.

Storage:

Store in a cool, dry well-ventilated place and keep in its' sealed original container. Protect from frost. The maximum storage life of this product is 24 months.

HEALTH & SAFETY:

This product is approved for use under the Biocidal Products Regulation [528/2012] - Authorisation No. UK-2016-1015

Contains PROPICONAZOLE - 0.24% w/w & 3-iodo-2-propynyl-n-butyl carbamate – 0.75% w/w;

EC Classification – **HARMFUL TO AQUATIC LIFE, MAY BE FATAL IF SWALLOWED & ENTERS AIRWAYS.**

HARMFUL – May cause lung damage if swallowed; Repeated exposure may cause skin dryness & cracking.

UNPROTECTED PERSONS AND ANIMALS SHOULD BE KEPT AWAY FROM TREATED AREAS FOR AT LEAST 48 HOURS.

Keep out of reach of children; Keep away from food, drink and animal feeding stuffs;

Keep away from sources of ignition - No smoking

**DANGER**

Storage & Packaging:

LANGLOW WOOD PRESERVATIVES are available in 1, 2.5, 5 & 25 litre steel cans. Store in cool, well-ventilated conditions, away from any direct sources of heat or ignition. For transport purposes LANGLOW WOOD PRESERVATIVES are classified as UN 1306 – Wood Preservative, Packing group III.

The information provided by this Technical data sheet is given in good faith and is to the best of our current knowledge true and accurate. However it is given without guarantee, as conditions of use and workmanship involved are both beyond our control. All information supplied is subject to the company's terms and conditions of sale, copies of which are available on request.