



MVIS™ Masonry Veneer Mortar

255 - 0818

Globally Proven
Construction Solutions



1. PRODUCT NAME MVIS Masonry Veneer Mortar

2. MANUFACTURER

LATICRETE UK
Speke Hall Industrial Estate
Speke, Liverpool, Merseyside, L24 1YA
United Kingdom
Tel: 0151 486 6101
Fax: 0151 448 1982
e-mail: sales@laticrete.co.uk
www.laticrete.co.uk

3. PRODUCT DESCRIPTION

MVIS Masonry Veneer Mortar is a patented, versatile polymer fortified mortar designed specifically for the installation of adhered masonry veneer, natural manufactured stone and thin brick. A high-performance mix provides maximum non-sag performance for vertical installations and also obtains maximum bond strength to the substrate and selected veneers. Reinforced with Kevlar® for added strength, MVIS Veneer Mortar offers exceptional workability and is backed by the Laticrete 25 Year Tile & Stone System Warranty.

Uses

- For vertical, horizontal and overhead installation of manufactured stone and thin brick veneers on exterior and interior installations.
- Ideal for both commercial and residential installations

Advantages

- Incredible non-sag performance even when high build up to 18mm giving faster, easier installations
- Revolutionary patented formula provides maximum bond strength to veneers and substrate—exceeds ANSI A118.4 requirements
- Exceeds ASTM C270 compressive strength requirements for masonry veneer installations
- Passes IBC and IRC shear bond strength code requirements for adhered masonry veneer when tested in accordance with ASTM C482
- Conforms to EN 12004 with a classification of C2 TE S1
- Mixes only with water – no admix needed
- Reinforced with Kevlar
- Lightweight mortar — very smooth and easy to apply
- GREENGUARD certified for low VOCs

Suitable Substrates

- Cement mortar (Scratch & brown coat)
- Concrete
- Concrete block
- Cement backer board*
- Masonry and brick

*Consult cement backer board manufacturer for specific installation recommendations and to verify acceptability for exterior use.

Packaging 15kg 54 per pallet

Colour

Grey

Approximate Coverage

Per 15 kg bag mixed with 5 litres of water

Trowel Size

Vertical Applications	m ²
(6 mm x 9 mm) notched trowel	3.8-4.5
(12 mm x 12 mm) notched trowel	2.8-3.3
Adhered Masonry Veneer Application Method	2.2-2.7

Shelf Life

Factory sealed containers of this product are guaranteed to be of first quality for one (1) year* if stored off the ground in a dry area.

* High humidity will reduce the shelf life of bagged product.

Limitations

- Mastics, adhesive mortars and pointing mortars for thin brick, masonry veneer, stone, pavers and thin brick are not replacements for waterproofing membranes or air and water barriers. When a waterproofing membrane or air and water barriers is required, use MVIS Air & Water Barrier (see data sheets DS 633.0 & DS 633.5 for more information).
- For veneer installations using this product, consult local building code requirements regarding limitations and installation system specifications.
- Not for use in submerged or steam room applications. For these applications use Hi-Bond Masonry Veneer Mortar.
- Use LATAPOXY® 300 Adhesive for installing green marble, Resin backed, or moisture sensitive tile, stone and agglomerates (refer to DS 633.0 for more information)

Note: Surfaces must be structurally sound, stable and rigid enough to support ceramic/stone tile, thin brick and similar finishes. Substrate deflection under all live, dead and impact loads, including concentrated loads, must not exceed L/360 for thin bed ceramic tile/brick installations or L/480 for thin bed stone installations where L=span length. For exterior vertical installations over framed construction, the substrate deflection under all live, dead and impact loads, including concentrated loads, must not exceed L/600 where L=span length (except where local building codes specify more stringent deflection requirements).

Cautions

Consult MSDS for more safety information.

- Some marbles and other stone have low flexural strength and might not be suitable for exterior installations, check with veneer manufacturer for suitability.
- During cold weather, protect finished work from traffic until fully cured.
- Contains portland cement and silica sand. May irritate eyes and skin. Avoid contact with eyes or prolonged contact with skin. In case of contact, flush thoroughly with water.
- DO NOT take internally. Silica sand may cause cancer or serious lung problems. Avoid breathing dust. Wear a respirator in dusty areas.
- For white and light-colored stone, conduct test area to ensure no shadowing or staining is observed.
- Keep out of reach of children.

4. TECHNICAL DATA

VOC/LEED Product Information



This product has been certified for Low Chemical Emissions (ULCOM/GG UL2818) under the UL GREENGUARD Certification Program For Chemical Emissions For Building Materials, Finishes and Furnishings (UL 2818 Standard) by UL Environment.

Total VOC Content pounds/gallon (grams/litre) of product is 0.00 g/ℓ.

Applicable Standard

ASTM C270, ANSI A118.4, ANSI A118.11, EN12004 C2 TE-S1

Physical Properties

Mixed with water [5.0 ℓ] per 15kg

Test	Test Method	EN 12004 C2 Specification	Results
28 day cure tensile adhesive strength	EN 12004	> 1.0 N/mm ²	1.9 – 2.1 N/mm ²
7 day cure 21 day water immersion tensile adhesive strength	EN 12004	> 1.0 N/mm ²	1.1–1.4N/mm ²
14 day cure 14 day heat age tensile adhesive strength	EN 12004	> 1.0 N/mm ²	2.0–2.8N/mm ²
7 day cure 21 day water immersion 25 freeze/thaw cycle tensile adhesive strength	EN 12004	> 1.0 N/mm ²	1.2–1.4 N/mm ²
Open time after 30 minutes	EN 12004	> 0.5 N/mm ²	1.5–1.7 N/mm ²
Slip	EN 12008	< 0.5 mm	< 0.5 mm
Transverse deformation	EN12002	> 2.5 mm and < 5 mm	3.1-3.3mm

Working Properties

Pot Life	4 hours
Wet Density	1.3 gm/cm ³

Specifications subject to change without notification. Results shown are typical but reflect test procedures used. Actual field performance will depend on installation methods and site conditions.

5. INSTALLATION

Surface Preparation

All surfaces should be between 40°F (4°C) and 90°F (32°C) and structurally sound, clean and free of all dirt, oil, grease, paint, concrete sealers or curing compounds. In exposed locations, the installation may require temporary protection from penetrating rain & wind-chill using frost blankets or waterproof sheets to sustain the required temperature throughout the curing process of the adhesive. Rough or uneven concrete surfaces should be made smooth with Premium Mortar Bed. Expansion joints shall be carried through the adhered manufactured stone masonry veneer (AMSMV) from all construction or expansion joints in the substrate. Do not cover expansion joints with mortar.

1. Installer must verify that deflection under all live, dead and impact loads of substrates does not exceed industry standards of L/600 for AMSMV units or stone installations where L=span length. For exterior vertical installations over framed construction, the substrate deflection under all live, dead and impact loads, including concentrated loads, must not exceed L/600 where L=span length.

Mixing – (15 kg) bag

Place approximately 5.0 ℓ of clean water in a pail and slowly add the entire bag of MVIS Masonry Veneer Mortar. Mix with slow speed mixer for one minute or until a creamy smooth consistency is reached. Allow to stand for 5 minutes, remix and use. Jobsite conditions might vary. Add slightly more water if necessary for proper consistency.

Application

See applicable LATICRETE details in LATICRETE® Veneer Installation System Brochure (DS 002.8).

Note: If installing on sheathed wood or steel frame construction with wire lath, use LATICRETE Premium Mortar Bed for the wall render prior to installing applicable waterproofing membrane or Masonry Veneer Mortar.

If waterproofing is required, install MVIS Air & Water Barrier as per instructions (see Data sheet DS 661.0) to the substrate prior to installation of MVIS Veneer Mortar.

For adhered masonry veneers use a hand trowel to apply a thin coat of MVIS Veneer Mortar to cover entire back of the veneer unit. Spread additional mortar onto the back of the skim coated veneer unit sufficient to completely fill the space between the veneer unit and the substrate when compressed against the substrate. Press the mortar covered back of the veneer against the substrate at the desired final position. Slide the unit roughly (25 - 38 mm) diagonally from the desired final position and back into the desired position while maintaining even pressure. This should be done in such a manner as to squeeze the mortar to fill the entire space between the veneer unit and the substrate, helping to achieve 100% coverage to both the substrate and veneer unit, allowing excess mortar to extrude on all sides around the veneer unit. Clean excess extruded mortar with trowel and spread onto the next veneer unit to be installed.

Note: Prior to installation, ensure back of veneer units are clean of dust, laitance, loose concrete crumbs and any excess film that could impede bond.

For adhered masonry veneer using a hand trowel to apply MVIS Masonry Veneer Mortar into the substrate thoroughly and then comb on additional mortar (trowel size is determined by substrate flatness and finished material size). Back butter all veneer units (200 mm x 200 mm) or larger to provide full bedding of the veneer. Place veneer into the mortar and adjust to desired position. Clean any excess mortar between veneers or sides of stone or tile veneer.

Note: Use proper sized notched trowel to ensure full bedding of the tile. Spread only enough mortar that can be covered with tile within 15–20 minutes. Adjust as necessary. Check mortar for complete coverage by periodically removing veneer unit and inspecting the transfer onto the back of the tile. The size and weight of the veneer will vary. Conduct a small test area for non-sag performance. Due to job site conditions and differences in finish material types; ledger boards, shims, wedges or spacers may be required to maintain finish levels and heights.

Grouting/Pointing

Point all joints within the installation after a minimum of 12–24 hours curing time at 70°F (21°C). Cooler temperatures require a longer curing time. Point all veneer joints with either Laticrete Masonry Pointing Mortar or Premium Masonry Pointing Mortar in accordance with the product instructions.

Cleaning

Clean tools with water.

6. AVAILABILITY AND COST

Availability

LATICRETE and LATAPOXY® materials are available worldwide. For on-line Distributor Information, call 0151 486 6101 or visit LATICRETE UK at www.laticrete.co.uk

7. MAINTENANCE

Non-finish LATICRETE and LATAPOXY installation materials require no maintenance but installation performance and durability may depend on properly maintaining products supplied by other manufacturers.

8. TECHNICAL SERVICES

Technical Assistance

Information is available by calling the LATICRETE UK Technical Service Hotline:

Tel: 0151 486 6101

Fax: 0151 448 1982

e-mail: sales@laticrete.co.uk

Technical and Safety Literature

To acquire technical and safety literature, please visit our website at www.laticrete.co.uk

9. DISCLAIMER

The information contained in this document is given in good faith and to the best of our knowledge is true and accurate.

This information is subject to change without notice and it is the responsibility of the user to obtain up to date and current information.

The use of this product is beyond our control and liability is assumed by the user when used incorrectly and not in accordance with LATICRETE guidelines.

The manufacturer is not responsible for any loss or damage arising from incorrect usage of this product.

The specifier or other party responsible for the project must ensure that the details in this data sheet are appropriate for the intended application and that additional detailing is performed for specific design or any areas that fall outside the scope of this specification.

LATICRETE International, Inc.

One LATICRETE Park North, Bethany, CT 06524-3423 USA • 1.800.243.4788 • +1.203.393.0010 • www.laticrete.com

©2013 LATICRETE International, Inc.

All trademarks shown are the intellectual properties of their respective owners.